

NAC-DS 1048

Wetting and Dispersing Additive (Solvent Based)

Polymeric wetting and dispersing additive for solvent-borne and solvent-free coating systems for stabilizing pigments (inorganic, organic and also effect pigments) and fillers. It results in high gloss; reduced floating/flooding, higher color strength, and strong reduction of millbase viscosity. NAC-DS 1048 used for all kinds of solvent-based coatings as well as pigment concentrates.

Product Data

Composition: Modified polyurethane

Typical Properties:

Note: This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product.

| | |
|---|---------------------|
| Physical Form: | Light yellow liquid |
| Active Content: | 40% |
| Density (20 °C): | 0.95-1.00 g/ml |
| Non-volatile matter (10 min., 150 °C): | 40% |

Applications

Applications > Recommended for > Particularly Recommended:

Coatings > Solvent based systems
> All kinds of resin systems (Alkyd, PU, Epoxy, Polyester, Nitrocellulose)

Recommended Levels:

Note: The properties and performance of the additive are greatly dependent upon the specific formulation in which it is utilized and, consequently, should always be tested (possibly at different treatment levels, temperatures, and/or time intervals) to verify performance before use.

| | |
|----------------------------------|----------|
| Based on | |
| Total formulation weight: | 0.2-0.5% |
| Titanium dioxide: | 2-3% |
| Inorganic pigments: | 3-5% |
| Organic pigments: | 5-8% |
| Carbon black: | 10-15% |

Special Feature:

Suitable for high gloss solvent-based systems

Incorporation and Processing Instructions:

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

Storage and Transportation:

Separation or turbidity may occur at low temperatures. Heat to 30-40 °C and stir. The minimum shelf life in closed containers is 12 months from the date of manufacture.

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.