

## **NAC-DS 1014**

## Wetting and Dispersing Additive (Solvent Based)

Very economically controlled flocculating wetting and dispersing additive with low dosage for solvent-based construction (Alkyd resin) coatings for stabilizing fillers, organic, inorganic, and carbon black pigments.

## **Product Data**

Composition:	Acrylic copolymer	
<b>Typical Properties:</b> <b>Note:</b> This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product.	Physical Form: Active Content: Density (20 °C): Non-volatile matter (10 min., 150 °C):	Brownish liquid 45-50% 0.95-1.00 g/ml 45-50%
Applications Applications > Recommended for > Particularly Recommended:	Coatings > Solvent based systems > Alkyd systems	
<b>Recommended Levels:</b> <b>Note:</b> The properties and performance of the additive are greatly dependent upon the specific formulation in which it is utilized and, consequently, should always be tested (possibly at different treatment levels, temperatures, and/or time intervals) to verify performance before use.	Based on Total formulation weight: Titanium dioxide: Organic pigments: Carbon black:	0.2% 2% 3-5% 6-8%
Special Feature:	Low dosage	
Incorporation and Processing Instructions:	For optimum performance, the additive must be incorporated into the mill base before the addition of pigments.	
Storage and Transportation:	Separation or turbidity may occur at low temperatures. Heat to 30-40 °C and stir. The minimum shelf life in closed containers is 12 months from the date of manufacture.	

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.